

Sponsor: Kimberly Tucker Cyberbond, LLC 401 N. Raddant Rd. Batavia IL 60510

Agar Overlay Final Report

Test Article: Apollo 2999
Purchase Order: 13243
Laboratory Number: 706777
Study Received Date: 12 Aug 2013

Test Procedure(s): Standard Test Protocol (STP) Number: STP0031 Rev 08

Summary: The Agar Overlay test was designed to determine the cytotoxicity of diffusible components from materials or solutions. A layer of agar was added over a cell monolayer to act as a cushion to protect the cells from mechanical damage while allowing the diffusion of leachable materials. The test articles were then placed on top of the agar layer and incubated. The cell monolayers were examined and scored based on the degree of cellular destruction. All test method acceptance criteria were met. The test procedure(s) listed above were followed without deviation.

Results:

Test Article:

Results		Sco	Amount Tootod		
Pass/Fail	#1	#2	#3	Average	Amount Tested
Pass	0	0	0	0	≥ 100 mm ² per well

Controls:

ld-uff-dis-		Sco	Amount Tootad		
Identification	#1	#2	#3	Average	Amount Tested
Negative Control – Polypropylene Pellets	0	0	0	0	≥ 100 mm² per well
Positive Control – Latex Natural Rubber	4	4	4	4	≥ 100 mm² per well

Acceptance Criteria: The United States Pharmacopeia & National Formulary (USP <87>) states that the test article meets the requirements if the reactivity grade is not greater than grade 2 or a mild reactivity. The ANSI/AAMI/ISO 10993-5 standard states that the achievement of a numerical grade greater than 2 is considered a cytotoxic effect. Nelson Laboratories acceptance criteria was based upon the negative control receiving "0" reactivity grades and positive control receiving 3-4 reactivity grades (moderate to severe).



Study Director

Bobbi L. Rushton-Castro

acj FRT0031-0001 Rev 3



Procedure: Six well cell culture plates were seeded with a verified quantity of industry standard L-929 cells (ATCC CCL-1) and incubated at $37 \pm 1^{\circ}$ C with $5 \pm 1\%$ CO₂ until approximately 80% confluent. The agar overlay consisted of an equal mixture of 1NAGAR (1.0%) and 2X MEM + 10% bovine calf serum. Solid test articles were placed directly on the solidified agar overlay testing \geq 100 mm² per test well. Positive and negative reference controls were included with each assay.

All tests were performed using three test wells per test article. After the addition of the test articles, the cell culture plates were incubated as described above for 24-26 hours. Following incubation, cells were evaluated microscopically using the evaluation criteria outline below:

Grade	Description Of Zone			
0	No detectable zone around or under the test article.			
1	Some malformed or degenerate cells under the test article.			
2	Zone limited to area under the test article and less than 0.45 cm beyond the test article.			
3	Zone extends 0.45 to 1.0 cm beyond the test article.			
4	Zone extends greater than 1 cm beyondfrom test article.			

The results from the three wells were averaged to give an average cytotoxicity score.