

TECHNICAL DATA SHEET

Cyberbond Europe GmbH

Werner-von-Siemens-Straße 2
D - 31515 Wunstorf

phone +49 / 50 31 / 95 66 - 0
fax +49 / 50 31 / 95 66 - 26

info@cyberbond.de
www.cyberbond.eu

Status: April 2015

CYBERBOND Blast 6070

Primer for Cyanoacrylate and UV Adhesives

Contents:

- 10 ml brush on glass bottle
- 500 ml plastic bottle
- 5 l container

Selling unit:

- 30 pieces
- 1 piece
- 1 piece

Chemical Base:

Heptane

Physical Data:

Density at 20 °C: 0.68 g/cm³

Flashpoint: -1 °C

Shelf life:

1 year in unopened containers

Description:

The Primer Cyberbond Blast 6070 enables you to bond unpolare materials such as e. g. Polyethylene (PE), Polypropylene (PP), Polyoxymethylen (POM), Silicone as well as modern Thermoplastic Elastomer (TPE) by means of Cyberbond Cyanoacrylate Adhesive.

In case of bonding Polycarbonate (PC) and Polymethylmethacrylat (PMMA) plastics Cyberbond Blast 6070 could significantly improve bonding results.

Cyberbond Blast 6070 changes the surface tension. The advantages are:

- high strength bonding of materials which could not be bonded before,
- a fast and easy to use method to support bonding,
- a higher flexibility of choosing materials.

Cyberbond 9056 will be brushed on the mating parts. After evaporation application of Cyberbond Cyanoacrylate Adhesive immediately can start. The parts also can be temporarily stored for 24 h.

Cyberbond Blast 6070 is ISO 10993-5 approved.

The data mentioned in this data sheet, particularly the recommendations for application and use of products are based on our recent knowledge and experience. Due to the fact of having so many different materials involved and conditions of applications which are out of our influence, we strongly recommend to do sufficient tests in order to guarantee that Cyberbond products are suitable for the intended process and applications. Except for wilful acts any liability based on such recommendations or any verbal advice is hereby expressly excluded.